

Oldrati's special FFKM compounds for Orings

Polymer base	Oldrati compound name	Hardness (Shore A)	Notes	Working Temperature range
FFKM	OLD REX P475N FG	70 ÷ 75	Very High Temperature service, compliant FDA	from -15°C (-20°C peak) up to +230°C (+240°C peak)
FFKM	OLD REX P480N	75 ÷ 80	Very High Temperature service	from -15°C (-20°C peak) up to +230°C (+240°C peak)
FFKM	OLD REX P490N	85 ÷ 90	Very High Temperature service	from -15°C (-20°C peak) up to +230°C (+240°C peak)
FFKM	OLD REX P495N	90 ÷ 95	Very High Temperature service AED approved acc. to NORSOK M-710 / Part B	from -15°C (-20°C peak) up to +230°C (+240°C peak)
FFKM	OLD REX P595N	90 ÷ 95	Outstanding High Temperature service	from -15°C (-20°C peak) up to +290°C (+300°C peak)
FFKM	OLD REX P590NHT	85 ÷ 90	Excellent High Temperature service and steam resistance	from -15°C (-20°C peak) up to +300°C (+320°C peak)